

SPECIFICATION AMENDMENTS:

Please amend the paragraphs that appear in the upper half of page 87 of the Specification and that encompass Table C-1 with the following amended paragraphs and Table C-1:

--

Table C-1

		Ex. C-1	Ex. C-2	Ex. C-3	Ref. Ex. C-1	Ref. Ex. C-2
Surface condition		Fine	Fine	Fine	Aggregate	Aggregate
Front surface resistivity Log (Ω /sq)	Average	10.28	10.51	10.34	7.01	8.84
	Standard deviation	0.15	0.07	0.03	0.05	0.10
Rear surface resistivity Log (Ω /sq)	Average	10.31	10.53	10.37	8.83	10.28
	Standard deviation	0.14	0.07	0.03	0.61	0.14
Volume resistivity Log (Ω -cm)	Average	8.63	8.63	8.92	9.64	8.7
	Standard deviation	0.07	0.04	0.06	0.26	0.2
Difference between rear surface resistivity and front surface resistivity in surface resistivities between front and rear surfaces	Index	0.02	0.02	0.03	1.82	1.44
Difference between front surface resistivity and volume resistivity in surface resistivities between front and rear surfaces	Index	1.66	1.88	1.42	-2.62	0.14
CB content (% by weight)		15.1	15.1	15.4	15.7	15.5
Average thickness (μ m)		100	100	100	100	100

--